

C-CURE

PRODUCT INFORMATION

BEST AVAILABLE COPY



COLORCURE 945

GROUT ADMIXTURE

PRODUCT DESCRIPTION

COLORCURE is a blend of latex-emulsions and special chemical modifiers that have been specifically formulated to greatly improve the physical working and performance characteristics of Portland cement based grouts. Used in lieu of water when mixing, COLORCURE will significantly improve bond strength, flexibility and resistance to frost, weather and thermal shock. COLORCURE is not only a latex admixture. It also chemically insures more complete hydration (curing) of Portland cement based grouts which inhibits the development of many of the grouting problems commonly encountered such as initial discoloration, color fading, powdering, cracking and efflorescence.

AREA OF USE

COLORCURE is used in lieu of water when mixing Portland cement based grouts. For best results, use C-Cure's AR, MP, or SUPREME grouts. COLORCURE may be used when grouting any type of tile, interior or exterior, on residential or commercial installations. COLORCURE is easier to clean than conventional latex admixtures.

LIMITATIONS

COLORCURE must not be diluted with water. Use in temperature range above 60°F. (Do not allow mortar to freeze for the first 72 hours).

APPLICABLE STANDARDS

COLORCURE, when used with any of C-Cure's grouts will meet all applicable standards for ANSI A118.6 and ANSI A108.10.

COLOR - White liquid.

TEXTURE - Free-flowing liquid.

PACKAGING - 4/1 gallon bottles, 5 gallon pails, 55 gallon drums.

INSTALLATION

PREPARATORY WORK

Wait a minimum of 48 hours before grouting a Dry-Set installation, 72 hours for a conventional installation and 48 hours for an adhesive installation. The width and depth of the joints should be the same. Excessive setting mortar above 1/3 the depth of the joints should be removed before grouting. It may be necessary to use shades or screens to prevent rapid water evaporation due to sun or wind. Check the grouting material on the exact tile being used to determine if a grout release is required.

MIXING

To a mixing container add approximately 1/2 gallon of COLORCURE per 25 pounds of powder. Add the grout to the COLORCURE and mix thoroughly by hand or with a low RPM power mixer insuring a uniform mix with no color streaks. Mechanical mixers must be 300 RPM or lower to avoid entraining air which will substantially weaken the mortar. Allow the grout to slake for 10 minutes, then remix. Do not retemper with liquid or powder after this point. Once the grout has become too stiff to work, it must be discarded and a new batch mixed.

APPLICATION

Due to the nature of this product, it will always be used in conjunction with a C-Cure grouting material which will have detailed installation procedures on the container. Apply grout mixed with COLORCURE in the normal fashion as directed on each bag of C-Cure grout. Normal cleaning with minimal water is all that is necessary.

WARRANTY

Manufacturers warranty is limited to replacement of defective material.

STORAGE LIFE

One year if kept in sealed containers, stored in a dry area.

PROTECT FROM FREEZING DURING STORAGE.

Safety—CAUTION: Avoid inhalation of vapors, use in well ventilated areas. Avoid contact with eyes, flush with water and call physician immediately. For skin contact, wash with warm soapy water. If material is swallowed, call physician immediately.

KEEP OUT OF REACH OF CHILDREN

GUARANTEE

The recommendations, suggestions, statements and technical data are based on the best knowledge available to C-CURE CORPORATION and are given for informational purposes ONLY and without any responsibility for their use. C-CURE CORPORATION MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO THE PRODUCT SOLD HEREIN except that the quality of the ingredients shall be in accordance with C-CURE CORPORATION specifications. It is expressly understood and agreed that the buyer's sole and exclusive remedy shall be replacement of defective products and under no circumstances shall C-CURE CORPORATION be liable for incidental or consequential damages. C-CURE CORPORATION neither assumes nor authorizes any others to assume for it any liability with respect to furnishing of the product. Handling and use of the product are beyond the control of C-CURE CORPORATION, therefore no warranty is made, express or implied, as to the results obtained from the use of the product or against any claims for infringement of patents resulting from use of the product.

This writing constitutes a complete and exclusive statement of the understanding between the C-CURE CORPORATION and buyer. There were no oral agreements or warranties, express or implied, collateral to or affecting the furnishing of the product. This understanding shall not be modified except in writing by an officer of C-CURE CORPORATION.

Members of National Tile Contractors Association, Materials & Methods Standards Association, Ceramic Tile Distributors Association.

NOTICE: The information in this bulletin is presented in good faith, but no warranty, express or implied, is given nor is freedom from any patent. In as much as any assistance furnished by C-Cure with reference to the safe use and disposal of its products is provided without charge, C-Cure assumes no obligation or liability therefore, except to the extent that any such assistance shall be given in good faith.

C-CURE CORPORATION
305 GARDEN OAKS, HOUSTON, TX 77018,
1-800-292-2874, (713) 697-2024,
FAX (713) 697-1622

Product Information #945DS070193
© Copyright 1993, C-Cure Corporation
Printed 1993

GROUT ADMIXTURE